

EMSL Canada Order:

Customer ID: Customer

PO:

Project ID:

Attn: Yevgeny Govshievich Phone: (514) 261-2434

YG Home Inspection Services Fax:

79 Rue Saint-Hubert Received: 3/ 7/2022

Chateauguay, QC J6K 3X8 Collected:

Analyzed: 3/ 7/2022

Project: 2842 A

Test Report: Asbestos Analysis by IRSST Method 244

Sample Name	Sample Description		Test/ Analysis Date	Non Asbestos		
		Color		Fibrous	Non Fibrous	Asbestos
1 EMSL -0001	Garage ceiling finishing material	Brown/ Various	PLM 3/ 7/2022	0.0%	100.0%	<1% Chrysotile
2- Floor Tile EMSL -0002	Closet floor tiles	Tan	PLM 3/ 7/2022	0.0%	98.0%	2% Chrysotile
2- Mastic EMSL -0002A	Closet floor tiles	Black	PLM 3/ 7/2022	0.0%	100.0%	None Detected
3 EMSL 6-0003	Basement ceiling finishing material	Brown	PLM 3/ 7/2022	0.0%	100.0%	None Detected

Analyst(s):

Stephen Mastromonaco PLM IRSST(4)

Reviewed and approved by:

Dmitriy Suzdalev, Labatory Manager or other approved signatory

IRSST Analytical Method 244 applicable asbestos concentration ranges are as follows: ND (none detected), Trace (4 or less fibers, possible contamination), <1%, 1 to 5%, from 5 to 10%, from 10 to 25%, from 50 to 75%, from 50 to 75% to 90%, >90%. Floor tiles reported as ND or Trace by PLM are required to be analyzed by TEM (method ELAP 198.4). The estimated limit of detection for non-detect samples is <0.1%. Due to limitations inherent in PLM, asbestos fibers with dimensions below the limit of resolution will not be detected. The above test report relates only to the items tested and may not be reproduced in any form without the express written approval of EMSL. EMSL's liability is limited to the cost of analysis. EMSL bears no responsibility for sample collection

Samples analyzed by EMSL Canada Inc. Ville Saint-Laurent, QC PLM IRSST: NVLAP Lab Code 201052-0, TEM IRSST: NYS ELAP Lab Code 12043

Initial report from: 3/8/2022